

■硬さ関係表

金属に関しては、様々な工業規格により異なる硬さ値間で換算がおこなえるテーブルが示されています。
なお、正確な結果は、あくまでも各試験機によるものを基準として考えてください。

●鉄鋼

ビッカース	ロックウェル				ロックウェル ファイナル			シヨア
	HV	HRA	HRB	HRC	HRD	15N	30N	
940	85.6	—	68.0	76.9	93.2	84.4	75.4	98.0
920	85.3	—	67.5	76.5	93.0	84.0	74.8	96.8
900	85.0	—	67.0	76.1	92.9	83.6	74.2	95.6
880	84.7	—	66.4	75.7	92.7	83.1	73.6	94.3
860	84.4	—	65.9	75.3	92.5	82.7	73.1	93.1
840	84.1	—	65.3	74.8	92.3	82.2	72.2	91.7
820	83.8	—	64.7	74.3	92.1	81.7	71.8	90.4
800	83.4	—	64.0	73.8	91.8	81.1	71.0	89.0
780	83.0	—	63.3	73.3	91.5	80.4	70.2	87.6
760	82.6	—	62.5	72.6	91.2	79.7	69.4	86.2
740	82.2	—	61.8	72.1	91.0	79.1	68.6	84.8
720	81.8	—	61.0	71.5	90.7	78.4	67.7	83.3
700	81.3	—	60.1	70.8	90.3	77.6	66.7	81.8
690	81.1	—	59.7	70.5	90.1	77.2	66.2	81.0
680	80.8	—	59.2	70.1	89.8	76.8	65.7	80.2
670	80.6	—	58.8	69.8	89.7	76.4	65.3	79.4
660	80.3	—	58.3	69.4	89.5	75.9	64.7	78.6
650	80.0	—	57.8	69.0	89.2	75.5	64.1	77.8
640	79.8	—	57.3	68.7	89.0	75.1	63.5	77.0
630	79.5	—	56.8	68.3	88.8	74.6	63.0	76.2
620	79.2	—	56.3	67.9	88.5	74.2	62.4	75.4
610	78.9	—	55.7	67.5	88.2	73.6	61.7	74.5
600	78.6	—	55.2	67.0	88.0	73.2	61.2	73.7
590	78.4	—	54.7	66.7	87.8	72.7	60.5	72.8
580	78.0	—	54.1	66.2	87.5	72.1	59.9	72.0
570	77.8	—	53.6	65.8	87.2	71.7	59.3	71.1
560	77.4	—	53.0	65.4	86.9	71.2	58.6	70.2
550	77.0	—	52.3	64.8	86.6	70.5	57.8	69.3
540	76.7	—	51.7	64.4	86.3	70.0	57.0	68.4
530	76.4	—	51.1	63.9	86.0	69.5	56.2	67.5
520	76.1	—	50.5	63.5	85.7	69.0	55.6	66.6
510	75.7	—	49.8	62.9	85.4	68.3	54.7	65.6
500	75.3	—	49.1	62.2	85.0	67.7	53.9	64.7
490	74.9	—	48.4	61.6	84.7	67.1	53.1	63.7
480	74.5	—	47.7	61.3	84.3	66.4	52.2	62.8
470	74.1	—	46.9	60.7	83.9	65.7	51.3	61.8
460	73.6	—	46.1	60.1	83.6	64.9	50.4	60.8
450	73.3	—	45.3	59.4	83.2	64.3	49.4	59.8
440	72.8	—	44.5	58.8	82.8	63.5	48.4	58.8
430	72.3	—	43.6	58.2	82.3	62.7	47.4	57.8
420	71.8	—	42.7	57.5	81.8	61.9	46.4	56.7
410	71.4	—	41.8	56.8	81.4	61.1	45.3	55.7
400	70.8	—	40.8	56.0	81.0	60.2	44.1	54.6
390	70.3	—	39.8	55.2	80.3	59.3	42.9	53.6
380	69.8	(110.0)	38.8	54.4	79.8	58.4	41.7	52.5
370	69.2	—	37.7	53.6	79.2	57.4	40.4	51.4
360	68.7	(109.0)	36.6	52.8	78.6	56.4	39.1	50.3
350	68.1	—	35.5	51.9	78.0	55.4	37.8	49.2
340	67.6	(108.0)	34.4	51.1	77.4	54.4	36.5	48.1
330	67.0	—	33.3	50.2	76.8	53.6	35.2	46.9
320	66.4	(107.0)	32.2	49.4	76.2	52.3	33.9	45.7
310	65.8	—	31.0	48.4	75.6	51.3	32.5	44.6
300	65.2	(105.5)	29.8	47.5	74.9	50.2	31.1	43.4
295	64.8	—	29.2	47.1	74.6	49.7	30.4	42.8
290	64.5	(104.5)	28.5	46.5	74.2	49.0	29.5	42.2
285	64.2	—	27.8	46.0	73.8	48.4	28.7	41.6
280	63.8	(103.5)	27.1	45.3	73.4	47.8	27.9	41.0
275	63.5	—	26.4	44.9	73.0	47.2	27.1	40.4
270	63.1	(102.0)	25.6	44.3	72.6	46.4	26.2	39.7
265	62.7	—	24.8	43.7	72.1	45.7	25.2	38.9
260	62.4	(101.0)	24.0	43.1	71.6	45.0	24.3	38.1
255	62.0	—	23.1	42.2	71.1	44.2	23.2	37.9
250	61.6	99.5	22.2	41.7	70.6	43.4	22.2	37.2
245	61.2	—	21.3	41.1	70.1	42.5	21.1	36.6
240	60.7	—	20.3	40.3	69.6	41.7	19.9	36.0
230	—	96.7	(18.0)	—	—	—	—	34.7
220	—	95.0	(15.7)	—	—	—	—	33.4
210	—	93.4	(13.4)	—	—	—	—	32.0
200	—	91.5	(11.0)	—	—	—	—	30.7
190	—	89.5	(8.5)	—	—	—	—	29.4
180	—	87.1	(6.0)	—	—	—	—	28.0
170	—	85.0	(3.0)	—	—	—	—	26.6
160	—	81.7	(0.0)	—	—	—	—	25.2
150	—	78.7	—	—	—	—	—	23.8
140	—	75.0	—	—	—	—	—	22.3
130	—	71.2	—	—	—	—	—	20.8
120	—	66.7	—	—	—	—	—	19.4
110	—	62.3	—	—	—	—	—	17.9
100	—	56.2	—	—	—	—	—	16.3

●黄銅

ビッカース	ロックウェル		ロックウェル ファイナル	
	HV	HRB	HRF	30T 45T
196	93.5	110.0	77.5	66.0
194	—	109.5	—	65.5
192	93.0	—	77.0	65.0
190	92.5	109.0	76.5	64.5
188	92.0	—	—	64.0
186	91.5	108.5	76.0	63.5
184	91.0	—	75.5	63.0
182	90.5	108.0	—	62.5
180	90.0	107.5	75.0	62.0
178	89.0	—	74.5	61.5
176	88.5	107.0	—	61.0
174	88.0	—	74.0	60.5
172	87.5	106.5	73.5	60.0
170	87.0	—	—	59.5
168	86.0	106.0	73.0	59.0
166	85.5	—	72.5	58.5
164	85.0	105.5	72.0	58.0
162	84.0	105.0	—	57.5
160	83.5	—	71.5	56.5
158	83.0	104.5	71.0	56.0
156	82.0	104.0	70.5	55.5
154	81.5	103.5	70.0	54.5
152	80.5	103.0	—	54.0
150	80.0	—	69.5	53.5
148	79.0	102.5	69.0	53.0
146	78.0	102.0	68.5	52.5
144	77.5	101.5	68.0	51.5
142	77.0	101.0	67.5	51.0
140	76.0	100.5	67.0	50.0
138	75.0	100.0	66.5	49.0
136	74.5	99.5	66.0	48.0
134	73.5	99.0	65.5	47.5
132	73.0	98.5	65.0	46.5
130	72.0	98.0	64.5	45.5
128	71.0	97.5	63.5	45.0
126	70.0	97.0	63.0	44.0
124	69.0	96.5	62.5	43.0
122	68.0	96.0	62.0	42.0
120	67.0	95.5	61.0	41.0
118	66.0	95.0	60.5	40.0
116	65.0	94.5	60.0	39.0
114	64.0	94.0	59.5	38.0
112	63.0	93.0	58.5	37.0
110	62.0	92.6	58.0	35.5
108	61.0	92.0	57.0	34.5
106	59.5	91.2	56.0	33.0
104	58.0	90.5	55.0	32.0
102	57.0	89.8	54.5	30.5
100	56.0	89.0	53.5	29.5
98	54.0	88.0	52.5	28.0
96	53.0	87.2	51.5	26.5
94	51.0	86.3	50.5	24.5
92	49.5	85.4	49.0	23.0
90	47.5	84.4	48.0	21.0
88	46.0	83.5	47.0	19.0
86	44.0	82.3	45.5	17.0
84	42.0	81.2	44.0	14.5
82	40.0	80.0	43.0	12.5
80	37.5	78.6	41.0	10.0
78	35.0	77.4	39.5	7.5
76	32.5	76.0	38.0	4.5
74	30.0	74.8	36.0	1.0
72	27.5	73.2	34.0	—
70	24.5	71.8	32.0	—
68	21.5	70.0	30.0	—
66	18.5	68.5	28.0	—
64	15.5	66.8	25.5	—
62	12.5	65.0	23.0	—
60	10.0	63.0	20.5	—
58	—	61.0	18.0	—
56	—	58.8	15.0	—
54	—	56.5	12.0	—
52	—	53.5	—	—
50	—	50.5	—	—
49	—	49.0	—	—
48	—	47.0	—	—
47	—	45.0	—	—
46	—	43.0	—	—
45	—	40.0	—	—

●この変換表は規格SAE J 417に基づいて編集しました。●シヨア硬さはJIS B 7731によります。